

# Technical Data Sheet

## Durite™ Resin AD-3231

### Description

AD-3231 is a pulverized, heat resistant, phenolic resin of the two-step type.

### Application

AD-3231 was specifically developed as a general-purpose bond for resinoid grinding wheels. It provides an optimum balance of room temperature, elevated temperature and wet strength properties. Used in conjunction with phenolic and/or furfural wetting agents, it has been used successfully as a bond in most types of grinding wheels.

### Typical Properties

Property	Value	Unit
Glass Plate Flow at 125°C	42 - 64	mm
Hexa Content	6.5 - 7.5	%
Hot Plate Cure at 150°C	70 - 100	Seconds
Particle Size <= 74 micron	96.5 - 99.5	% vol.

Tests are made in accordance with the current Hexion Standard Test Method and are available upon request.

### Storage

AD-3231 is a stable material with little tendency to sinter when stored in closed containers in a cool (21° C / 70° F), dry location.

### Handling

This product has to be used and disposed of according to the indications given in its safety data sheet. Hexion Inc. solid products, including but not limited to powders and flake resin products, can be combustible and present a fire or explosion hazard under certain conditions (including, but not limited to when dusts are finely divided and suspended in air and/or allowed to accumulate on surfaces). Fine dust clouds may form explosive mixtures. The buyer must comply with all laws, regulations and standards applicable to the possession, handling and use of solid products by the buyer. Please consult US NFPA Standard 652 & 654, UK HSE Guidance HSG 103, or other national guidance on safe handling of combustible dusts.

### Packaging

AD-3231 is available in 60-gallon, fiber drums containing approx. 250 pounds net (4 drums per pallet).

### Note

As part of our quality assurance efforts, we ensure compliance with the indicated product parameters at the time of shipping. Phenolic resins are known to be subject to a process of change that depends on the storage and transportation conditions. Even when the material is stored at the conditions indicated above, the useful life must be individually verified by the user of our products.