

# Technical Data Sheet

## EPIKURE™ Curing Agent 3175

### Product Description

EPIKURE™ Curing Agent 3175 is a modified polyamide supplied at 100 percent solids. It is designed for use with epoxy resins to formulate high solids, two-component, ambient cure coatings. Coatings based on this resin offer long-term corrosion resistance and excellent chemical resistance.

### Benefits

- Rapid cure response
- Good working pot life
- Long-term corrosion resistance
- Excellent chemical and solvent resistance

### Sales Specifications

Property	Value	Unit	Test Method
Amine Value	300 - 380	mg/g	ASTMD2896
Color	9	Gardner	ASTMD1544
Viscosity at 25°C	X-Z1		ASTMD-1625

### Typical Properties

Property	Value	Unit	Test Method
Density	7.87	lbs/gal	ASTMD1475
Equivalent Weight Approx.	103		
Flash Point, Setflash	>200	°F	
Nonvolatiles	100	%	

### General Information

EPIKURE Curing Agent 3175, when combined with a liquid epoxy resin like EPON™ Resin 828, produces coatings which exhibit a high level of performance while providing formulated VOC's of less than 3.0 pounds/gallon. The VOC may be lowered through the use of reactive, low viscosity, epoxy functional modifiers such as HELOXY™ Modifier 68 or HELOXY Modifier 107. The use of these modifiers, while improving VOC, may have some effect on performance and should be evaluated on an individual basis.

This product does not contain non-reactive diluents or extenders, which provides the formulator with greater latitude in choosing solvents or diluents for a particular application. The pot life of primer formulations using EPIKURE Curing Agent 3175 with EPON Resin 828 varies from 4 to 10 hours depending on formulated viscosity. Formulations for brush and roll application (80-90 KU) will have a usable pot life of approximately four hours, while those prepared at spray viscosity (65-75 KU) will be usable for approximately 10 hours.

A combining ratio of 65% liquid epoxy (WPE=190) and 35% EPIKURE Curing Agent 3175 based on solids, represents a stoichiometric or 1/1 equivalence and provides the best overall performance for most applications.

EPIKURE Curing Agent 3175  
<https://www.hexion.com/en-US/product/epikure-curing-agent-3175>

Generated: May 27, 2022  
 Issue Date:  
 Revision: 8/1/2007 12:00:00 AM

© and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

## Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion, Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

## Packaging

Available in bulk and drum quantities.

## Contact Information

For product prices, availability, or order placement, please contact customer service:

[www.hexion.com/Contacts/](http://www.hexion.com/Contacts/)

For literature and technical assistance, visit our website at [www.hexion.com](http://www.hexion.com)