

Technical Data Sheet

EPIKURE™ Curing Agent 3370

Product Description

EPIKURE™ Curing Agent 3370 is a low viscosity, modified cycloaliphatic amine capable of effecting thorough cures in epoxy resin systems at normal room temperature.

Application Areas/Suggested Uses

- Light color castings
- Chemical resistant glaze, sealer and gel coatings
- Industrial floor toppings
- Tank linings

Benefits

- Good overnight cure development
- Moderate resistance to blush or "sweat-out"
- High degree of chemical resistance
- Light color

Sales Specifications

Property	Value	Unit	Test Method
Amine Value	384 - 407	mg/g	ASTMD2896
Color	1	Gardner	ASTMD1544
Viscosity at 25°C	85 - 145	cP	ASTMD2196

Typical Properties

Property	Value	Unit	Test Method
Density	8.33	lbs/gal	ASTMD1475
Equivalent Weight Approx.	72		
Flash Point, Setflash	>200	°F	

Performance Properties

Table 1 / Properties of epoxy resin systems cured with EPIKURE Curing Agent 3370

Composition	Units	A	B	C	D	E	F
EPON™ Resin 828	pbw	100	–	–	–	80	80
EPON Resin 813	pbw	–	100	–	–	–	–
EPON Resin 8132	pbw	–	–	100	–	–	–
EPON Resin 8101	pbw	–	–	–	100	–	–
HELOXY™ Modifier 48	pbw	–	–	–	–	20	–
HELOXY Modifier 505	pbw	–	–	–	–	–	20
EPIKURE Curing Agent 3370	pbw	38	38	36	38	40	33

Handling Properties @ 25°C

Viscosity, System	cP	2,000	475	475	460	1,300	1,375
Gel Time, 100 gram mass	min	25	29	41	30	28	35
Peak Exotherm, 100 gram mass	°C	201	190	177	–	197	160

Cured State Properties ¹

Heat Deflection Temperature	°C	56	48	47	54	53	49
Tensile Strength	psi	10,700	8,200	5,200	8,100	10,300	7,000
Tensile Elongation at break	%	2.5	13.0	50.0	29.0	2.7	23.0
Tensile Modulus	ksi	560	430	260	310	530	350
Flexural Strength	psi	16,200	12,800	7,500	10,400	–	–
Flexural Modulus	ksi	560	400	230	300	–	–
Flexural deflection	in.	0.18	>0.60	>0.60	>0.60	–	–
Compressive Strength, Ultimate	psi	19,200	15,100	19,000	27,000	–	–
Compressive Strength, Yield	psi	17,300	14,000	7,800	10,700	–	–

EPIKURE Curing Agent 3370
<https://www.hexion.com/en-US/product/epikure-curing-agent-3370>

Generated: January 21, 2020
Issue Date:
Revision:

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Composition	Units	A	B	C	D	E	F
Izod impact, notch	ft.·lb./in.	0.42	0.39	0.64	0.54	0.51	0.67
Hardness	Shore D	90	88	84	87	90	50
Glass Bow Shrinkage Test	inch/inch	fail	pass	–	–	–	–
Chemical Resistance ²							
Water, distilled	%	0.13	0.20	0.29	0.22	0.17	0.21
5% Acetic Acid	%	0.21	0.29	0.44	0.29	0.41	0.29
Xylene	%	0.05	1.85	7.45	–	0.03	1.18

¹All systems were cured for 7 days at 25 °C.

²Values reported as percent weight gain after immersion for 24 hours.

Table 2/Chemical resistance¹ of EPON Resin 828 cured with EPIKURE Curing Agent 3370

	1 Day	1 Week	1 Month	3 Months
Water	0.12	0.32	0.65	1.22
5% Detergent	0.10	0.31	0.63	1.18
5% Acetic acid	0.18	0.49	1.03	1.90
20% Acetic acid	1.62	4.54	8.862	Destroyed
50% Acetic acid	6.87	Destroyed	–	–
99.7% Acetic acid	5.69	Destroyed	–	–
10% Sulfuric acid	0.30	0.74	1.43	2.45
25% Sulfuric acid	0.25	0.67	1.33	2.46
70% Sulfuric acid	0.24	0.44	0.88	1.85
98% Sulfuric acid	Destroyed	–	–	–
5% Nitric acid	0.23	0.59	1.13	2.03

EPIKURE Curing Agent 3370

<https://www.hexion.com/en-US/product/epikure-curing-agent-3370>

Generated: January 21, 2020

Issue Date:

Revision:

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

	1 Day	1 Week	1 Month	3 Months
20% Nitric acid	0.46	1.17	2.20	3.84
10% Hydrochloric acid	0.19	0.47	0.91	1.70
10% Sodium hydroxide	0.09	0.26	0.51	0.94
50% Sodium hydroxide	0.00	0.00	-0.06	-0.08
5% Citric acid	0.13	0.34	0.68	1.25
5% Lactic Acid	0.13	0.38	0.72	1.33
Methyl ethyl ketone	Destroyed	–	–	–
Xylene	0.04	0.06	0.09	0.18
Toluene	0.04	0.09	0.19	0.59
Ethanol	0.79	3.06	6.87 ³	Destroyed
Methanol	4.31	Destroyed	–	–
Isopropanol	-0.01	-0.01	0.03	0.21
Gasoline	0.03	0.04	0.06	0.11
Antifreeze	0.00	-0.02	-0.05	-0.05
Brake fluid	0.13	0.49	1.58	4.37
Transmission fluid	0.05	0.08	0.10	0.15 ²
Skydrol (500B4)	0.01	-0.01	-0.01	0.03
Bleach	0.10	0.23	0.46	0.92
3% Hydrogen peroxide	0.12	0.36	0.76	1.51
50% Sugar solution	0.10	0.28	0.56	1.05

¹Reported as percent weight change of immersed 1" x 3" x 1/8" samples at 25 °C.

²Moderate swelling and slight softening.

³Moderate swelling and softening.

Table 3/ The effect of modifier addition on the properties of EPON Resin 828 /EPIKURE Curing Agent 3370 systems

Composition	Units	A	B	C	D	E
EPON Resin 828	pbw	100	100	100	100	100
Nonylphenol	pbw	-	-	-	-	20
Benzyl alcohol	pbw	-	20	-	-	-
Dibutyl phthalate	pbw	-	-	20	-	-
Piccoclastic A-5 ¹	pbw	-	-	-	20	-
EPIKURE Curing Agent 3370	pbw	42	42	42	42	42
Handling Properties @ 25°C						
Viscosity, System	cP	165	90	90	310	1,000
Gel Time, 100 gram mass	min	24	24	45	44	18
Cured State Properties ²						
Heat Deflection Temperature	°C	54	28	47	52	50
Tensile Strength	psi	10,500	2,850	5,700	10,250	9,050
Tensile Elongation at break	%	2.4	44.0	28.5	3.4	5.7
Tensile Modulus	ksi	550	130	290	510	450
Izod impact, notch	ft.·lb./in.	0.47	1.23	0.46	0.4	0.45
Hardness	Shore D	90	80	86	89	89
Chemical Resistance ³						
Water, distilled	%	0.18	0.39	0.39	0.12	0.09
5% Acetic Acid	%	0.27	0.72	0.72	0.20	0.30

EPIKURE Curing Agent 3370
<https://www.hexion.com/en-US/product/epikure-curing-agent-3370>

Generated: January 21, 2020
Issue Date:
Revision:

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Composition	Units	A	B	C	D	E
Xylene	%	0.06	0.47	0.47	0.53	1.32

¹Supplied by Hercules, Inc.

²All systems were cured for 7 days at 25 °C.

³Percent weight gain after immersion for 24 hours at 25 °C.

General Information

EPIKURE Curing Agent 3370 is an effective curing agent for many epoxy resins including both reactive diluent-modified and conventional bisphenol A types. Table 1 lists the cured state and handling properties for a typical system cured with EPIKURE 3370. The effects of the lower epoxide functionality of the diluent-containing EPON[®] Resin 813, EPON 8132, and EPON 8101 are reflected by significant increases in extensibility (flexibility), and decreases in strength modulus and solvent resistance.

The resistance of a EPON 828/EPIKURE 3370 system to long term exposure to a variety of chemicals at room temperature is illustrated in Table 2. These data confirm a significant improvement in overall chemical resistance compared to systems cured with typical aliphatic amine-based curing agents.

EPIKURE 3370 can be combined with most aliphatic and cycloaliphatic curing agents to modify handling characteristics or cured state performance. Blending with EPIKURE 3271 or EPIKURE 3274 has been found to be particularly effective in altering the reactivity. Ultimate performance characteristics of such combinations depend on the level of modification and the performance profile of the aliphatic amine curing agent selected.

In many applications, the excellent cured state properties of epoxy systems cured with EPIKURE Curing Agent 3370 allow for modification with non-reactive diluents to lower the system cost. Laboratory studies have shown that in most cases, properties are not critically affected by modifier concentrations of up to 20 parts by weight per hundred parts of resin (phr). The effects on handling and cured state properties of an EPON 828/EPIKURE 3370 system when modified with 20 phr of various commercially available nonreactive diluents are shown in Table 3.

EPIKURE Curing Agent 3370 is hygroscopic. Depending on the surface-to-mass relationship, partially-filled, uncapped containers of this curing agent can absorb as much as ten weight percent of atmospheric moisture during an overnight storage period. Absorbed moisture readily complexes with this curing agent and results in the formation of a "skin" or sludge agglomeration on the surface. Once sludge formation occurs, the curing agent can only be reclaimed by removal of the solid by filtration or by blending it with fresh curing agent and heating to temperatures not to exceed 250 °F until the solid material reliquifies. Therefore, EPIKURE Curing Agent 3370 based systems must be stored in containers with tightly fitted lids to minimize exposure to the atmosphere prior to use.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at www.hexion.com

EPIKURE Curing Agent 3370
<https://www.hexion.com/en-US/product/epikure-curing-agent-3370>

Generated: January 21, 2020
Issue Date:
Revision:

© and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.