

Technical Data Sheet

EPIKURE™ Curing Agent 3202

Product Description

EPIKURE™ Curing Agent 3202 is a modified aliphatic amine. It is compatible with both reactive diluent modified epoxy resins and conventional bisphenol A epoxy resins. EPIKURE 3202 is compatible and can be used in combination with most aliphatic and cycloaliphatic amine curing agents to modify handling characteristics or cured state properties.

Application Areas/Suggested Uses

- General purpose casting and encapsulation
- Low VOC

Benefits

- Low viscosity
- High reactivity at room temperature
- Low color
- Good chemical resistance

Sales Specifications

Property	Value	Unit	Test Method
Amine Value	1.225 - 1.525	mg/g	ASTMD2896
Color	9	Gardner	ASTMD1544

Typical Properties

Property	Value	Unit	Test Method
Density	8.20	lbs/gal	ASTMD1475
Equivalent Weight Approx.	37	AHEW	
Non-volatile materials	100.0	% by Weight	
Viscosity @ 25°C	20	cP	ASTMD2196

¹ Brookfield Viscometer - Small Sample Adapter, about 10 grams.

² Weight per Gallon Cup.

Performance Properties

Table 1 / Properties of EPON Resin 828 cured with EPIKURE Curing Agent 3202

EPIKURE Curing Agent 3202
<https://www.hexion.com/en-US/product/epikure-curing-agent-3202>

Generated: May 17, 2022
 Issue Date:
 Revision: 8/1/2007 12:00:00 AM

© and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

	Method	Units	Value
EPON Resin 828		pbw	100
EPIKURE Curing Agent 3202		pbw	20

Handling Properties @ 25°C

Gel Time, 100 gram mass	SHYODU Gel Timer	min	21
Cure Schedule		hrs @ 25 °C	24
		hrs @ 100 °C	2

Cured State Properties			
Heat Deflection Temperature ¹	ASTM D648	°C	109
Tensile Strength ²	ASTM D638	psi	10,046
Tensile Elongation		%	10.7
Tensile Modulus		ksi	381
Hardness ³	ASTM D2240	Durometer D	86

Chemical Resistance⁴

Water		%	0.2
5% Acetic Acid		%	1.8
50% Xylene/50% Isopropanol		%	0.0

¹ HDT ASTM D648 (Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position)

² ASTM D638 (Tensile Properties of Plastics)

³ ASTM D2240 (Standard Test Method for Rubber Property-Durometer Hardness)

⁴ Percent weight gain after immersion for 24 hours @ 25°C - specimen size 1/8" X 1" X 3"

General Information

EPIKURE 3202 is an effective converter for most types of epoxy resin. It has a tendency to form complexes with atmospheric carbon dioxide, particularly in humid conditions, and can be formulated, adducted or otherwise reacted to inhibit amine blush.

EPIKURE Curing Agent 3202
<https://www.hexion.com/en-US/product/epikure-curing-agent-3202>

Generated: May 17, 2022
Issue Date:
Revision: 8/1/2007 12:00:00 AM

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at www.hexion.com