

# Technical Data Sheet

## Durite™ Resin FD-2170

### Description

FD-2170 is a powdered, heat resistant, phenolic resin of the novolac type.

### Application

FD-2170 was specifically developed as a general-purpose bond for friction elements. FD-2170 has excellent hot molding latitude and is utilized in both asbestos and non-asbestos compositions.

### Typical Properties

Property	Value	Unit	Test Method
Free Phenol Calculated	1.8 - 2.8	%	
Glass Plate Flow	29 - 43	mm	IR-009
Hexa Content	7.5 - 8.5	%	IR-280
Hot Plate Cure 150°C	70 - 90	sec	IR-008
Particle Size	97 - 99	% thru 200 Mesh	IR-010

### Storage

FD-2170 is a stable material with little tendency to sinter when stored in closed containers in a cool (70° F), dry location.

Tests are made in accordance with the current Hexion Standard Test Method as identified.

NOTE: Organic powders can be combustible under certain conditions, consult NFPA 652 and NFPA 654 when handling this product or any other organic powder.

### Packaging

FD-2170 is available in moisture resistant 50-pound bags (2,000 pounds per pallet), 20 kg bags (2,204 kgs per pallet) and 1,000 kg bulk bags.

Durite™ Resin FD-2170

<https://www.hexion.com/en-US/product/durite-resin-fd-2170>

Generated: April 20, 2024

Issue Date:

Revision: 7/5/2018 1:00:00 PM

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.