

EPIKURE™ Curing Agent 3164

EPIKURE Curing Agent 3164

Product Description

EPIKURE™ Curing Agent 3164 is a proprietary oligomeric polyamine curing agent for structural applications. Epoxy resins cured with EPIKURE Curing Agent 3164 can produce films, castings, or adhesive joints with a high degree of toughness and flexibility.

Benefits

- Imparts highly flexible properties
- Improved toughness compared to conventional polyamines
- Improved combinations of elongation, strength, modulus, abrasion resistance, and tear resistance in comparison with those given by other "flexibilizing" curing agents
- Strong low temperature properties of cured formulations
- Good adhesion to a variety of substrates
- Resistant to surface blush and amine exudates
- Useful as formulating tool in blending with other curing agents to impart desired properties

Sales Specifications

Property	Standard	Value	Unit	Test Method
Amine Value		230 - 250	mg/g	ASTM D2896
Color		12	Gardner	ASTM D1544
Viscosity at 25°C		7000 - 11000	cP	ASTM D2196

Typical Properties

Property	Standard	Value	Unit	Test Method
Density		8.2	lbs/gal	ASTM D1475
Equivalent Weight		256	AHEW	
Flash Point, Setaflash		>200	°F	

EPIKURE Curing Agent 3164
<https://www.hexion.com/en-US/product/epikure-curing-agent-3164>

Generated: February 20, 2018
Issue Date:
Revision: August 01,2007

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Performance Properties

Table 1 / Properties of systems cured with EPIKURE Curing Agent 3125 and other "Flexibilizing" curing agents

Composition	Method	Units	1	2	3	4	5	6	7	8	9
Resin											
EPON™ Resin 828										80	75
EPON Resin 8132							80				
EPON Resin 58134			100	100	100	100		100	100		
EPON Resin 58034										20	
HELOXY™ Modifier 61							20				
HELOXY Modifier 505											25
Curing agent											
EPIKURE Curing Agent 3125 ¹			67	114	200	275	180				
EPIKURE Curing Agent 3055									42		
EPIKURE Curing Agent 3072										32	
EPIKURE Curing Agent 3046											42
EPIKURE Curing Agent 3266								133			
Handling Properties @ 25°C											
Viscosity, Resin		cP	600	600	600	600	600	600	45,000	6,775	2,340
Viscosity, Curing agent		cP						500	225	700	200
Gel Time, 100 gram mass		min.							133	49	245
Mechanical properties @ 25 °C²											
Tensile Strength	D638	psi	4,350	2,610	99	25	308	168	6,666	7,674	5,646

EPIKURE Curing Agent 3164
<https://www.hexion.com/en-US/product/epikure-curing-agent-3164>

Generated: February 20, 2018
 Issue Date:
 Revision: August 01,2007

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Tensile Elongation at break		%	13	98	111	208	121	149	5.1	3.4	15
Tensile Modulus		ksi	251	44	0.16	0.04	0.36	154	313	346	253
Tear strength	D624	lb/in	97	399	35	13	157	74	103	109	106
Izod impact, notched	D256	lb/in					10.7		0.6	0.6	0.8
Lap shear strength		psi ³									
Al-Al, 7 days ambient cure							1,032		1,831	550	1,524
Al-Al, 16 hr amb + 2 hr at 100 °C							1,615		1,833	866	2,625
Oily steel, 7 days ambient cure							1,166		1,617	599	1,589
Oily steel, 16 hr amb + 2 hr at 100 °C							2,130		1,608	774	2,233

¹Viscosity 10,000 cP, ASTM D 445 at 40 °C.

²Systems cured 24 hours at 25 °C plus 2 hours at 100 °C.

³ASTM D 1002

Table 2/ Properties of EPON Resins 828 and 815C cured with EPIKURE Curing Agent 3164 and EPIKURE Curing Agent 3163

Composition	Method	Units	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
EPON Resin 828			100		100	
EPON Resin 815C				100		100
EPIKURE Curing Agent 3163			195	198		
EPIKURE Curing Agent 3164					136	138

Handling Properties @ 25°C

Viscosity, Resin	cP	12,500	600	12,500	600
Viscosity, Curing agent	cP	145,000	145,000	8,200	8,200
Viscosity, Blend	cP	92,000	30,500	8,400	3,900
Gel Time, 100 gram mass	min.	45	53	49	82

EPIKURE Curing Agent 3164
<https://www.hexion.com/en-US/product/epikure-curing-agent-3164>

Generated: February 20, 2018
Issue Date:
Revision: August 01,2007

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Mechanical properties @ 25 °C¹

Tensile Strength	D638	psi	4,354	1,470	3,782	332
Tensile Elongation at break		%	169	240	189	260
Tensile Modulus		psi	218,000	8,112	213,000	168
Tear strength	D624	lb/in	934	521	1017	153
Taber abrasion		mg loss/ 1000 cycles	33	49	29	37
Izod impact, notch		ft-lb/in	0.8	23.0	1.4	19.6
Izod impact, un-notch	D256	ft-lb/in	11.6	Did Not Break	15.2	Did Not Break
Hardness, Shore D		24 hrs	66	38	24	–
		2 days	68	43	52	6
		7 days	72	57	72	42

Lap shear strength

Al-Al, 7 days ambient cure		psi ²	1,160	1,608	1,002	951
Al-Al, 16 hr amb + 2 hr at 100 °C		psi ²	3,068	2,060	3,003	932
Oily steel, 7 days ambient cure		psi ²	732	1,303	653	843
Oily steel, 16 hr amb + 2 hr at 100 °C		psi ²	2,598	1,854	2,189	936
Peel strength ³ Alum-Alum		lb/in	14	9.4	8.8	9.5
Water resistance		24 hrs	1.00	1.81	0.42	1.01
		7 days	2.90	4.81	1.40	2.56

¹Systems cured 24 hours at 25 °C plus 2 hours at 100 °C.

²ASTM D 1002

³ASTM D 1867, 180 (Peel Adhesion, 20 inches/minute)

General Information

EPIKURE Curing Agent 3164 is a proprietary oligomeric polyamine curing agent designed for use with epoxy resins to produce films, castings or adhesive joints with a high degree of toughness and flexibility. It is supplied as a solvent-free liquid.

The superior toughness and flexibility provided by EPIKURE Curing Agent 3164 in comparison with standard "polyamide" curing agents such as EPIKURE Curing Agent 3125, as well as a selection of other curing agents for "flexible" or "toughened" epoxy systems, is apparent from a comparison of Tables 1 and 2. This toughness and flexibility is achievable over a wide stoichiometric range. Some chemical resistance data for systems cured with EPIKURE Curing Agent 3164 are also shown in Table 2.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at: www.hexion.com

EPIKURE Curing Agent 3164
<https://www.hexion.com/en-US/product/epikure-curing-agent-3164>

Generated: February 20, 2018
Issue Date:
Revision: August 01,2007

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.