

# Technical Data Sheet

## Bakelite® Resin PF7268CL

### Description

Alkylphenol novolac solution in aromatic hydrocarbons

### Application

PF7268CL is used in fuel and lube additives, oilfield dispersants and demulsifiers

### Typical Properties

Property	Value	Unit
Flash Point 10- 370°C	ca. 62°C	
Höppler Viscosity at 20°C	200 – 800 mPa·s	
Karl Fischer water content	max 0.2%	
Resin Content	52 – 56%	
Specific gravity at 20°C	ca. 0.94	

Tests are made in accordance with the current Hexion Standard Test Method and are available upon request. The typical properties provided are examples of product attributes and may not be tested.

### Storage

PF7268CL should be useable for 9 months when stored at 18-20°C. Material should be mixed prior to use.

### Handling

This product has to be used and disposed of according to the indications given in its safety data sheet.

### Packaging

200kg drum, tank car

### Note

As part of our quality assurance efforts, we ensure compliance with the indicated product parameters at the time of shipping. Phenolic resins are known to be subject to a process of change that depends on the storage and transportation conditions. Even when the material is stored at the conditions indicated above, the useful life must be individually verified by the user of our products.

Bakelite Resin PF7268CL

<https://www.hexion.com/en-US/product/bakelite-resin-pf7268cl>

Generated: January 21, 2020

Issue Date:

Revision:

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.