

Technical Data Sheet

EPI-REZ™ Resin 3515-W-60 Europe

Product Description

EPI-REZ Resin 3515-W-60 is a moderate viscosity, non-ionic, aqueous dispersion of a bisphenol A epoxy resin. EPI-REZ Resin 3515-W-60 is supplied at typically 60 percent non-volatiles and is mechanically stable. No organic solvents are present.

Application Areas/Suggested Uses

EPI-REZ Resin 3515-W-60 offers a solvent-free approach to the formulation of for example:

- Industrial textile binders of fibre finishes
- Adhesives
- Coatings and electrical dip coatings
- Varnishes.

It can also be incorporated into formulations which are traditionally water-based and which require good strength and outstanding chemical or water resistance. EPI-REZ Resin 3515-W-60 is used to modify polymer lattices, especially those containing sufficient amine or carboxyl functionality to react with available epoxy groups.

EPI-REZ Resin 3515-W-60 can be cured with many of the same curing agents that are used with liquid or solution epoxy resins. Curing agents most conveniently employed are those which are water soluble or dispersible and which are stable in an aqueous medium. Examples of such curing agents include dicyandiamide, substituted imidazoles, aliphatic and aromatic amines and various EPIKURE Curing agents.

When applied at room temperature, EPI-REZ Resin 3515-W-60 coalesces to form a clear, continuous, tacky film after evaporation of the water.

Benefits

- High epoxy functionality
- Water reducible, providing wide latitude for viscosity reduction
- Imparts good chemical and water resistance properties
- Compatible with most synthetic polymer lattices
- Curable with most water soluble curing agents

Sales Specifications

Property	Value	Unit	Test Method
Epoxy Group Content	3636 - 4444	mmol/kg	ASTMD1652
Particle Size Cl, Dv (Vol Mean)	0.5 - 1.3	µm	SRC - 1
pH	3 - 6		ASTME70
Solids	62 - 64	% m/m	ASTMD1259
Viscosity* at 25°C	4000 - 15000	mPa.s	ASTMD2196

* Brookfield

Typical Properties

EPI-REZ Resin 3515-W-60 Europe
<https://www.hexion.com/en-US/product/epi-rez-resin-3515-w-60-europe>

Generated: January 27, 2022
 Issue Date:
 Revision: 1/1/2007 12:00:00 AM

© and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Property	Value	Unit	Test Method
Density at 25°C	1.103	kg/L	ASTMD4052
Epoxy Equivalent	225 - 275	g/eq*	ASTMD1652
Solvent	water		

* Number of grams of resin containing 1 equivalent of epoxide (Weight per equivalent, WPE, is an alternative term).

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

EPI-REZ Resin 3515-W-60 should be stored in tightly sealed containers in a dry location at temperatures between 10 and 38°C. Under these conditions the shelf life should be a minimum of one year from date of certification. Elevated temperatures or freezing conditions will accelerate particle settling which will require re-dispersion with moderate agitation. Do not allow the product to freeze.